

ABSTRACT OF THE DISCLOSURE

5 A porous resin film which is obtained from a compound
prepared by kneading a composition comprising 30 to 100% by weight
of a thermoplastic resin comprising a hydrophilic thermoplastic
resin and 0 to 70% by weight of an inorganic and/or an organic
powder in an intermeshing twin-screw extruder at a screw shear
rate of 300 sec^{-1} or higher and which has a liquid absorbing
capacity of 0.5 ml/m^2 or more as measured in accordance with
10 the method specified in Japan TAPPI Standard No. 51-87.